

PRODUCT SPECIFICATION

1521 BLOCK

Binder Synthetic Rubber
Colour Black
Cork Granule Size 1/2mm



**LA CASA
DEL CORCHO.**

Test Method	Property	Unit	Value
ASTM F 1315	Density	Kg/m3	560 – 760
ASTM D 2240	Hardness	Shore A	50 – 70
ASTM F 36	Compressibility at 400 PSI	%	35 – 50
ASTM F 36	Recovery at 400 PSI (min)	%	80
ASTM F 152	Tensile Strength (min)	MPa	0.96
ASTM F 147	Flexibility		
	Original (F=5)	-	No Cracks
	Oven aged, 70h at 100°C (F=16)	-	No Cracks
	ASTM N°1 Oil, 70h at 100°C (F=16)	-	No Cracks
ASTM F 146	Volume change after immersion		
	ASTM N°1 Oil, 70h at 100°C	%	-10 to +10
	IRM 903 Oil, 70h at 100°C	%	+10 to +40
	ASTM Fuel A, 22h at RT	%	0 to +15
ASTM F 146	Thickness Change, IRM 903 Oil, 70h at 100°C	%	-2 to +15
ASTM D 395	Compression Set, Method A, 22h at 70°C (max)	%	55